Frimpeks


TECHNICAL DATA SHEET

653037201 ECO THERMAL FSC (BPA FREE)-H400-YG

Face A white, non-topcoated FSC mix credit thermal paper that is coated with black imaging thermosensitive coating. This paper has limited resistance to thermal image scratching or smudging with normal stability against oil, alcohol and environmental influences such as heat, humidity and light. The image may fade over a period of time if exposed to high humidity and light. This paper is BPA-free.

Adhesive General-purpose permanent rubber based hotmelt adhesive. Provides high-bond strength on multiple substrates with enhanced performance also at low temperatures. Features excellent converting properties: ideal for high-speed slitting, matrix-stripping and automated dispensing. Suitability check advised before full-scale use.

Liner Yellow, supercalendered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in utomatic dispensing system.



Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m^2	70	
Thickness	ISO 534	µm	74	
Adhesive				
Peel adhesion 90°	FTM 2 st. st	N/m	320	(8 N/25mm)
Loop Tack	FTM 9 glass	N/m	640	(16 N/25mm)
Min. appl. Temperature		°C	0	
Service Temperature		°C	-30 / +60	
Liner				
Basis Weight	ISO 536	g/m^2	53	
Thickness	ISO 534	µm	46	
Transparency	DIN 53147	%	49	
Laminate				
Thickness	ISO 534	µm	130 ± %10	
Slit Rolls				
Width	ISO 534	mm	± 1	
Roll length measurement	ISO 534	m	± %1	

Application and Use

Typical applications are information labelling such as logistics and warehousing, stores mainly on paper, cardboard, plastic bags. Limited resistance to moisture, oil , fats and plasticizers and short term durability recommended for strong lighting to avoid image fade.

Conversion and Printing

This product has good printability in all classical printing methods. Printing inks should be checked for suitability prior to use. This product is designed for use in thermal printing system at printing speeds up to 10 inch /250 mm per sec (based on printer's set up).

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

One year when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

Disclaimer: The statements listed on this publication are according to our best knowledge. The statements do not exonerate the user from their own responsibility to determine that our products are suitable for their processes. All specific substrate specifications may vary by ±10%. They are intended to inform and advise and are subject to influence from the technical process. This edition with the indicated date below replaces all previous editions. With the present edition all older editions are null and void.