

653007501 ECO THERMAL (BPA FREE)-DF710-YG

Face A white, non-topcoated thermal paper that is coated with black imaging thermosensitive coating. This paper has limited resistance to thermal image scratching or smudging with normal stability against oil, alcohol and environmental influences such as heat, humidity and light. The image may fade over a period of time if exposed to high humidity and light.

Adhesive Acrylic based, permanent adhesive suitable for deep freeze applications onto cold and moist surfaces with very good adhesion at low temperature. Not suitable for labelling curved surfaces.

Liner Yellow, supercalendered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.



ECO THERMAL (BPA FREE)	
DF710	
YG	

Face	Method	Unit	Target
Basis Weight	ISO 536	g/m ²	70
Thickness	ISO 534	µm	74

Adhesive

Peel adhesion 90°	FTM 2 st. st	N/m	240	(6 N/25mm)
Loop Tack	FTM 9 glass	N/m	400	(10 N/25mm)
Min. appl. Temperature		°C	-20	
Service Temperature		°C	-40 / +60	

Liner

Basis Weight	ISO 536	g/m ²	53
Thickness	ISO 534	µm	46
Transparency	DIN 53147	%	49

Laminate

Thickness	ISO 534	µm	132 ± %10
-----------	---------	----	-----------

Slit Rolls

Width	ISO 534	mm	± 1
Roll length measurement	ISO 534	m	± %1

Application and Use

This product is designed for food labelling at low temperature and deep freeze conditions.

Conversion and Printing

This product has good printability in all classical printing methods. Printing inks should be checked for suitability prior to use. This product is designed for use in thermal printing system at printing speeds up to 10 inch /250 mm per sec (based on printer's set up).

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

One year when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

Disclaimer: The statements listed on this publication are according to our best knowledge. The statements do not exonerate the user from their own responsibility to determine that our products are suitable for their processes. All specific substrate specifications may vary by ±10%. They are intended to inform and advise and are subject to influence from the technical process. This edition with the indicated date below replaces all previous editions. With the present edition all older editions are null and void.