

654102850 PP WHITE 60 TC-W0820-PET CLEAR 23

Face	A white pearlescent, topcoated polypropylene film with high brilliance and internal reflectivity.
Adhesive	Acrylic based adhesive designed to wash off of glass, PP, PE and HDPE containers using industrial cleaning processes with hot, alkali water.
Liner	A clear polyester liner giving optimum smoothness to the adhesive layer. High strength and uniform quality permit very high speed conversion and dispensing.



PP WHITE 60 TC	
W0820	
PET CLEAR 23	

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m ²	42	
Thickness	ISO 534	µm	60	
Adhesive				
Peel adhesion 90°	FTM 2 st. st	N/m	200	(5 N/25mm)
Loop Tack	FTM 9 glass	N/m	400	(10 N/25mm)
Min. appl. Temperature		°C	+ 5	
Service Temperature		°C	- 20 / + 80	
Liner				
Basis Weight	ISO 536	g/m ²	32	
Thickness	ISO 534	µm	23	
Transparency	DIN 53147	%	-	
Laminate				
Thickness	ISO 534	µm	95 ± %10	
Slit Rolls				
Width	ISO 534	mm	± 1	
Roll length measurement	ISO 534	m	± %1	

Application and Use

This product is designed for applications where wash off labels are required for retail and logistics purposes. The washing time is dependant of the washing conditions.

Conversion and Printing

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing, recommended for digital printing.

Packaging

The rolls are sliced according to customer requirements; double sided siliconized papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22°C ± 2°C with a relative humidity of 50 %, ± 5%.

Disclaimer: The statements listed on this publication are according to our best knowledge. The statements do not exonerate the user from their own responsibility to determine that our products are suitable for their processes. All specific substrate specifications may vary by ±10%. They are intended to inform and advise and are subject to influence from the technical process. This edition with the indicated date below replaces all previous editions. With the present edition all older editions are null and void. This TDS is "Provisional"