



# Frimpeks LED UV Curable Varnishes

101694 LED-UV COATINGS FLEXO GLOSS 14001

# **Product Information**

101694 is a contemporary low energy/LED UV curable topcoat specially designed to work with Flexographic applications. This coating is specially formulated in order to match the needs of higher wavelength output of low energy/LED processes. Typically this coating has outstanding flow and leveling properties and has excellent curing capability. It creates an even, smooth surface with high gloss and high scuff resistance, with superior flexibility for scoring and folding.

#### Typical End Use

**Typical Properties** 

Magazines, Posters, Brochures, Leaflets, Packaging, Labels

# Low Viscosity, Solvent Free, can be further processed immediately

Gluable/Imprintable No	
Flexibility Ver	ry Good
Suitable Hot Stamping No	
Suitable for In-Line Yes	S
Can be Applied via Pump Yes	3
Suitable Direct Food Contact No	

#### **Technical Data**

Viscosity @ 22°C Ford Cup Reactivity with LED Solid Content 65 – 75 sec 385 / 395 nanometers 100 %

# **Recommended Application**

This coating is designed to be applied through various application systems including roller coater, flexo, letterpress, and roll-to-roll offset presses.

Recommended application is approximately  $3-4 \text{ gr/m}^2$  in order to get the optimal performance.

#### Processing

Stir properly for longer time under high shear, making sure that equipment is clean in order to avoid contamination from other materials.

# **Equipment and Drying**

This coating is designed to be cured at 385 / 395 nanometers LED lamp. Substrate may also have an effect on cure speed. Always test coating for compatibility with ink systems, substrates and for sufficient cure before general use.

#### Cleaning

Appliance and other equipment can be cleaned with alcohol or other UV cleaning products.

Liquid Appearance Odor Cured Appearance Gloss Hazy Typical Clear Film 90+ at 60° Reflection

# **Shelf Life and Storage Conditions**

UV Products must be stored tightly closed, away from direct light<sup>\*</sup>. The optimal storage temperature is between 5°C and 35°C. UV Products are packaged leaving sufficient air space to prevent accidental polymerization of the product. \*LED products are more sensitive to visible light .NORMAL STORAGE DURATION: 1 year

#### Safety

UV Products are generally considered to be non-toxicological. However during handling and use the user should avoid inhalation of vapors as well as direct eye or skin contact. UV products can be an irritant to skin and eyes, wash immediately with soap and water if there is direct contact. Protective eyewear and latex gloves are recommended while using this product. Consult the SDS for additional handling and safety information.

# Packaging

This product is available in: 20 KG pails 200 KG Iron Drums 1000 KG IBC

# Transportation

Non-dangerous goods. Can be transported in freezing temperatures but product should be brought to room temperature prior to use.

Disclaimer:

The statements listed on this publication are according to our best knowledge. The statements do not exonerate the user from their own responsibility to determine that our products are suitable for their processes. They are intended to inform and advise and are subject to influence from the technical process. This edition of April 22, 2023 replaces all previous editions. With the present edition all older editions are null and void.

Frimpeks Kimya ve Etiket Sanayi Ticaret A.S.

Velimeşe Organize Sanayi Bölgesi Mah. 236. sok. No:7/1Ergene - Tekirdağ/ Turkey T +90 282 674 5200 - frimpeks.com - uv@frimpeks.com