



# Frimpeks UV Curable Varnishes

11102 UV COATINGS GLOSS INK TRAIN 11102-DO

### **Product Information**

11102 is a UV curable coating specially designed to work on Offset applications. It is designed to be applied through the Ink Train of an Offset Press. Typically this coating has excellent flow and leveling properties and has excellent curing capability. It creates and even, smooth surface with high gloss and high scuff resistance, with high flexibility for scoring and folding.

# **Typical End Use**

Magazines, Posters, Brochures, Leaflets, Packaging, Labels

# **Typical Properties**

Dry Offset, Solvent Free, can be further processed immediately

# At a Glance

Gluable/Imprintable No Flexibility Good Suitable Hot Stamping Nο Suitable for In-Line No Can be Applied via Pump No Suitable Direct Food Contact No

### **Technical Data**

Viscosity @ 22°C Ford Cup 410 - 420 sec Reactivity with 120 W/cm<sup>2</sup> Lamp 60mi/cm<sup>2</sup> Solid Content 100%

# **Recommended Application**

This high viscosity coating is designed to be applied through the ink train of an offset press. It is also recommended for sheet-fed offset presses running with in-line UV coating capabilities. The use of a water-based primer to achieve greater coating qualities is advised. Recommended application is approximately 3-4 gr/m² in order to get the optimal performance.

### **Processing**

Stir properly for longer time under high shear, making sure that equipment is clean in order to avoid contamination from other materials.

# **Equipment and Drying**

This coating is designed to be cured at 60mj/cm<sup>2</sup> with 1-120 Watt/cm<sup>2</sup> lamp. Greater press speed and curing capability may be achieved with additional UV lamps. Substrate may also have an effect on cure speed. Always test coating for compatibility with ink systems, substrates and for sufficient cure before general use.

Appliance and other equipment can be cleaned with alcohol or other UV cleaning products.

Liquid Appearance Gardner 1 Typical Odor **Cured Appearance** Clear film

95+ at 60° Reflection

# Shelf Life and Storage Conditions

UV Products must be stored tightly closed, away from sunlight. The optimal storage temperature is between 5°C and 35°C. UV Products are packaged leaving sufficient air space to prevent accidental polymerization of the product. NORMAL STORAGE DURATION: 1 year

# Safety

UV Products are generally considered to be non-toxicological. However during handling and use the user should avoid inhalation of vapors as well as direct eye or skin contact. UV products can be an irritant to skin and eyes, wash immediately with soap and water if there is direct contact. Protective eyewear and latex gloves are recommended while using this product. Consult the SDS for additional handling and safety information.

# **Packaging**

This product is available in: 20 KG pails 200 KG Iron Drums

# **Transportation**

Non-dangerous goods. Can be transported in freezing temperatures but product should be brought to room temperature prior to

The statements listed on this publication are according to our best knowledge. The statements do not exonerate the user from their own responsibility to determine that our products are suitable for their processes. They are intended to inform and advise and are subject to influence from the technical process This edition of April 29, 2023 replaces all previous editions. With the present edition all older editions are null and void.