

Technical Information

Frimpeks UV Curable Varnishes

100664 UV SCREEN EMBOSS SEMI GLOSS 13557

Product Information

100664 is a UV curable coating specially designed for Screen applications. It can be used on both Rotary and Flatbed Screen applications. Typically this coating has outstanding flow and leveling properties and has excellent curing capability. It creates an even, smooth, highly raised, embossed surface with semi-gloss effect.

Typical End Use

Magazines, Posters, Brochures, Leaflets, Packaging, Labels

Typical Properties

Solvent Free, can be further processed immediately

At a Glance

Gluable/Imprintable	No
Flexibility	Very Good
Suitable Hot Stamping	No
Recommended Mesh	77/53
Can be Applied via Screen	Yes
Suitable Direct Food Contact	No

Technical Data

Viscosity @ 22°C Rheometer	3.50 – 4.50 pas
Reactivity with 120 W/cm ² Lamp	80mj/cm ²
Solid Content	100%

Liquid Appearance	Hazy White
Odor	Typical
Cured Appearance	Semi Clear Film
Gloss	70+ at 60° Reflection

Recommended Application

This coating is designed to for Screen applications. It can be used in both Rotary and Flatbed Screen applications.

Recommended application is approximately 7-10 gr/m² in order to get the optimal performance and gloss.

Processing

Stir properly for longer time under high shear, making sure that equipment is clean in order to avoid contamination from other materials.

Equipment and Drying

This coating is designed to be cured at 80mj/cm² with 1-120 Watt/cm² lamp. Greater press speed and curing capability may be achieved with additional UV lamps. Substrate may also have an effect on cure speed. Always test coating for compatibility with ink systems, substrates and for sufficient cure before general use.

Cleaning

Appliance and other equipment can be cleaned with alcohol or other UV cleaning products.

Shelf Life and Storage Conditions

UV Products must be stored tightly closed, away from sunlight. The optimal storage temperature is between 5°C and 35°C. UV Products are packaged leaving sufficient air space to prevent accidental polymerization of the product. NORMAL STORAGE DURATION: 1 year

Safety

UV Products are generally considered to be non-toxicological. However during handling and use the user should avoid inhalation of vapors as well as direct eye or skin contact. UV products can be an irritant to skin and eyes, wash immediately with soap and water if there is direct contact. Protective eyewear and latex gloves are recommended while using this product. Consult the SDS for additional handling and safety information.

Packaging

This product is available in:
20 KG pails
200 KG Iron Drums

Transportation

Non-dangerous goods. Can be transported in freezing temperatures but product should be brought to room temperature prior to use.

Disclaimer:

The statements listed on this publication are according to our best knowledge. The statements do not exonerate the user from their own responsibility to determine that our products are suitable for their processes. They are intended to inform and advise and are subject to influence from the technical process.

This edition of June 12, 2023 replaces all previous editions. With the present edition all older editions are null and void.

Frimpeks Kimya ve Etiket Sanayi Ticaret A.S.

Velimeşe Organize Sanayi Bölgesi Mah. 236.sok. No:7/1 Ergene - Tekirdağ / Turkey
T +90 282 674 5200 - frimpeks.com - uv@frimpeks.com