



## 652404500

# VELLUM EXTRA SAND. -PE300/PE300- YG/YG D 652404500

<ul> <li>sized, calendered woodfre</li> </ul>	ee printing paper with s	mooth surface.
•	sized, calendered woodfre	sized, calendered woodfree printing paper with s

Adhesive Acrylic based, strong permanent adhesive for general use. This adhesive gives excellent initial tack and

adhesion even on a wide variety substrates including apolar, rough and curved substrates. Edge

bleeding may occur.

Liner Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion,

punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m²	70 ± 3	
Thickness	ISO 534	μm	67 ± 3	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min.275	(min. 6,875 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.550	(min. 13,75 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +80	
Liner				
Basis Weight	ISO 536	g/m²	60 ± 2	
Thickness	ISO 534	μm	51 ± 3	
Transparency	DIN 53147	%	49	
Laminate				
Thickness	ISO 534	μm	195 ± 5	

#### **Application and use**

This sandwich construction consisting of usually two self-adhesive layers on top of each other (additional layers possible on request) Functional label applications where a second (or third) self adhesive label is needed when the first layer has been peeled off or applied e.g. promotional stickers on consumer products.

### **Conversion and Printing**

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

### **Packaging**

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

### **Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22  $^{\circ}$ C  $\pm$  2  $^{\circ}$ C with a relative humidity of 50 %,  $\pm$  5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

Document Number: TDS- 1398 Date of Publication: 01.01.2016 Rev.No:02 Rev.Date: Page Number: 1/1