

**654103210**
**PP WHITE 60 TC2 -DF710- WG\_D**
**654103210**

<b>Face</b>	A white pearlescent, topcoated polypropylene film with high brilliance and internal reflectivity.
<b>Adhesive</b>	Acrylic based, permanent adhesive suitable for deep freeze applications onto cold and moist surfaces with very good adhesion at low temperature. Not suitable for curved surface labelling.
<b>Liner</b>	White, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	44 ± 2	
Thickness	ISO 534	µm	60 ± 3	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.220	(min. 5,5 N/25mm)
Loop Tack	FTM 9 glass	N/m	min.400	(min. 10 N/25mm)
Min. appl temperature		°C	-20	
Service temperature		°C	-40 / +70	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	60 ± 2	
Thickness	ISO 534	µm	51 ± 3	
Transparency	DIN 53147	%	51	
<b>Laminate</b>				
Thickness	ISO 534	µm	125 ± 5	

**Application and use**

This product is designed for pre-packed food labeling at low temperature and deep freeze conditions.

**Packaging**

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

**Conversion and Printing**

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing.

**Shelf Life and Storage Conditions**

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.