

**655002600**
**PE OPAQUE 85 TC2 -WS820- WG\_D 655002600**

<b>Face</b>	A white opaque, topcoated polyethylene film that has very good die cutting performance.
<b>Adhesive</b>	Acrylic based, permanent, non-bleeding adhesive with improved water resistance, good clarity, UV resistance and short term removability.
<b>Liner</b>	White, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	80 ± 5	
Thickness	ISO 534	µm	80 ± 5	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min. 240	(min. 6 N/25mm)
Loop Tack	FTM 9 glass	N/m	min. 500	(min. 12,5 N/25mm)
Min. appl temperature		°C	+5	
Service temperature		°C	-20 / +100	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	60 ± 2	
Thickness	ISO 534	µm	53 ± 3	
Transparency	DIN 53147	%	51	
<b>Laminate</b>				
Thickness	ISO 534	µm	147 ± 5	

### Application and use

For use in labelling of quality products such as luxury items, cosmetics, toiletries and household chemicals requiring durability and resistance to chemicals or moisture. Due to its flexibility the product is especially suitable for substrates like plastic bags, squeezable bottles and other flexible containers.

### Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

### Conversion and Printing

Topcoated surface is suitable for printing by the usual printing technologies including letterpress, flexo, gravure and screen printing.

### Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

### Frimpeks Kimya ve Etiket Sanayi Ticaret Anonim Şirketi

Mermerciler Sanayi Sitesi T +90 212 867 1000 frimpeks.com.tr  
 8. Cad. No.:15 Beylikdüzü, F +90 212 875 1277 info@frimpeks.com.tr  
 34524 İstanbul/Turkey

ISO 9001:2008 Certificate No: TR09/000944