

651701610
PHARMA 60 -P100- WG_D
651701610

| | |
|-----------------|--|
| Face | A semi gloss white, one side coated, lightweight, calandered woodfree printing paper. |
| Adhesive | Acrylic based, permanent adhesive for general use. Suitable for numerous applications on clean, dry and flat surfaces, including slightly rough and curved substrates. It's not suitable for wet applications. Excellent performance during slitting, high speed matrix-stripping and automatic labelling. |
| Liner | White, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system. |

| Face | Method | Unit | Target | |
|-----------------------|---------------|------------------|---------------|---------------------------------|
| Basis Weight | ISO 536 | g/m ² | 62 ± 3 | |
| Thickness | ISO 534 | µm | 54 ± 3 | |
| Adhesive | | | | |
| Peel adhesion 90° | FTM 2 st.st | N/m | min.380 or PT | (min. 9,5 N/25mm or Paper Tear) |
| Loop Tack | FTM 9 glass | N/m | min.550 | (min. 13,75 N/25mm) |
| Min. appl temperature | | °C | 0 | |
| Service temperature | | °C | -20 / +80 | |
| Liner | | | | |
| Basis Weight | ISO 536 | g/m ² | 60 ± 2 | |
| Thickness | ISO 534 | µm | 53 ± 3 | |
| Transparency | DIN 53147 | % | 51 | |
| Laminate | | | | |
| Thickness | ISO 534 | µm | 115 ± 5 | |

Application and use

Specially developed for the pharmaceutical industry and for labelling products with small diameters and curved surfaces.

Conversion and Printing

Surface is suitable for excellent printing quality by all conventional print technologies and thermal transfer printing.

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

Frimpeks Kimya ve Etiket Sanayi Ticaret Anonim Şirketi

Mermereçiler Sanayi Sitesi T +90 212 867 1000 frimpeks.com.tr
 8. Cad. No.:15 Beylikdüzü, F +90 212 875 1277 info@frimpeks.com.tr
 34524 İstanbul/Turkey

ISO 9001:2008 Certificate No: TR09/000944