

653101005
TOP THERMAL -P100- YG_D
653101005

Face	A white topcoated paper that is coated with black imaging thermosensitive coating. This paper has very good resistance to moisture, oil, fat, alcohol and plasticizers.
Adhesive	Acrylic based, permanent adhesive for general use. Suitable for numerous applications on clean, dry and flat surfaces, including slightly rough and curved substrates. It's not suitable for wet applications. Excellent performance during slitting, high speed matrix-stripping and automatic labelling.
Liner	Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

Face	Method	Unit	Target	
Basis Weight	ISO 536	g/m ²	78 ± 5	
Thickness	ISO 534	µm	82 ± 5	
Adhesive				
Peel adhesion 90°	FTM 2 st.st	N/m	min.380 or PT	(min. 9,5 N/25mm or Paper Tear)
Loop Tack	FTM 9 glass	N/m	min.550	(min. 13,75 N/25mm)
Min. appl temperature		°C	0	
Service temperature		°C	-20 / +80	
Liner				
Basis Weight	ISO 536	g/m ²	60 ± 2	
Thickness	ISO 534	µm	53 ± 3	
Transparency	DIN 53147	%	49	
Laminate				
Thickness	ISO 534	µm	140 ± 5	

Application and use

Typical applications are information labelling such as price and weigh marking in stores (e.g. fruit, vegetable, deli), other retail use as well as any applications where short life or low contamination is common. (like retail and logistics labels for address, warehouse). We recommend to avoid its contact with plasticizers (PVC) and fat.

Conversion and Printing

Suitable for water based flexo printing. We recommend to check suitability for other printing methods. This product is designed for use in thermal printing system at printing speeds up to 10 inch /250 mm per sec (based on printer's set up).

Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

Shelf Life and Storage Conditions

One year when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

Frimpeks Kimya ve Etiket Sanayi Ticaret Anonim Şirketi

Mermerciler Sanayi Sitesi T +90 212 867 1000 frimpeks.com.tr
 8. Cad. No.:15 Beylikdüzü, F +90 212 875 1277 info@frimpeks.com.tr
 34524 İstanbul/Turkey

ISO 9001:2008 Certificate No: TR09/000944