

**651801805**
**VACUUM METALLISED SILVER TC3 -H400- YG\_D 651801805**

<b>Face</b>	A bright silver, vacuum metallised woodfree printing paper with a glossy print receptive lacquer.
<b>Adhesive</b>	Rubber based hotmelt, permanent adhesive for general use. Excellent adhesive performance on a wide variety of substrates including apolar, slightly rough and curved substrates. Particularly good performance at lower temperatures, we recommend to check suitability prior to use. Excellent performance during slitting, high speed matrix-stripping and automatic labelling.
<b>Liner</b>	Yellow, supercalandered siliconised glassine paper. Specially designed for high speed conversion, punching and perforation. Transparency allows its use in automatic dispensing system.

<b>Face</b>	<b>Method</b>	<b>Unit</b>	<b>Target</b>	
Basis Weight	ISO 536	g/m <sup>2</sup>	80 ± 3	
Thickness	ISO 534	µm	67 ± 3	
<b>Adhesive</b>				
Peel adhesion 90°	FTM 2 st.st	N/m	min.240 or PT	(min. 6 N/25mm or Paper Tear)
Loop Tack	FTM 9 glass	N/m	min.480	(min. 12 N/25mm)
Min. appl temperature		°C	0	
Service temperature		°C	-30 / +70	
<b>Liner</b>				
Basis Weight	ISO 536	g/m <sup>2</sup>	60 ± 2	
Thickness	ISO 534	µm	53 ± 3	
Transparency	DIN 53147	%	49	
<b>Laminate</b>				
Thickness	ISO 534	µm	128 ± 5	

### Application and use

This product suitable for primary labelling of high and luxury goods like wines, spirits, beverages, foods, stickers and promotional labelling.

### Packaging

The rolls are sliced according to customer requirements, double sided siliconised papers are put between of rolls. Paperboards are placed at the sides. They are delivered on pallets. Product description labels are fixed on rolls.

### Conversion and Printing

Suitable to flexo, letterpress, gravure and screen printing. Overvarnishing is recommended to improve durability of print and surface. Exposing to high temperature might have negative influence on face material's gloss.

### Shelf Life and Storage Conditions

Two years when stored away from direct sunlight and heat, in a dark, dry place at a temperature of 22 °C ± 2 °C with a relative humidity of 50 %, ± 5%.

All information and recommendations about Frimpeks products are based on our existing knowledge and experiences but do not mean a guarantee or warranty. As the products are used for different applications we recommend checking suitability of product prior to use. All information is subject to change without notice. End user obliged and verifies the above information before using the material.

### Frimpeks Kimya ve Etiket Sanayi Ticaret Anonim Şirketi

Mermerciler Sanayi Sitesi T +90 212 867 1000 frimpeks.com.tr  
 8. Cad. No.:15 Beylikdüzü, F +90 212 875 1277 info@frimpeks.com.tr  
 34524 İstanbul/Turkey

ISO 9001:2008 Certificate No: TR09/000944